

Adifix

Technical Data Sheet

Fissativo isolante universale per interni ed esterni.

Waterborne, concentrated, sealing primer that forms an alkali-resistant, insulating film, improving the adhesion and the resistance of the finishing coat.



INTENDED USE

Surface preparation of new walls in concrete, masonry, cement, lime or gypsum plasters or where old paints are not sufficiently sound.



SURFACE TREATMENT

Surface to treat must be clean, dry and even. Where necessary effect repairs on cracks or voids and if needed level the surface.



APPLICATION

Brush or roller.



THINNING

Add 5 or 6 parts of water to 1 part of ADIFIX.



AVERAGE SPREAD RATE

about 40 - 50 sq.m./litre per coat Variable, according to the absorption of the substrate



DRYING TIME AT 25° C

1 hour, touch dry

Recoat time: 4 - 5 hours



SPECIFIC GRAVITY

1000 ± 20 g/l



VISCOSITY

(DIN Cup 4, 20°C): 20"



ADVICES

Do not apply with air and surface temperatures below 5°C. or above 28°C.



PAKAGING

plastic bottles of lt. 1x6 units;

drums of lt. 4 and lt. 14;



DRY SOLID CONTENTS

(%): 25 ± 1



V.O.C. (Directive 2004/42/CE)

10 g/l; Cat. H BA (Max.Value 30 g/l)

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

