

Adismalt Opaco

Technical Data Sheet

Mat enamel paint for interiors and exteriors

Prime quality enamel paint for interiors and exteriors in Matt finish, featuring excellent hide, brushability and flow. It provides a hard wearing, durable finish with lasting resistance to yellowing and to weathering



Ver. 1



INTENDED USE

Finish coat for metal, timber and masonry surfaces.



SURFACE TREATMENT

New wood: Apply a coat of ADIPAC. Sand down and clean.

Prepainted wood: remove any loose paint, sand down and clean.

New iron surfaces: Wire brush the surface to remove any rust. Clean away all traces of dust, grease, oil and dirt then promptly apply ADIMIN or ANTIRUST primer

Prepainted iron surfaces: Scrape off all loose paint, wire brush, sand down and clean then promptly apply the antirust ADIMIN or ANTIRUST primer.

Stainless steel, galvanized and zinc coated surfaces, PVC: a coat of FUND FLEX.



COLOR

Supply colours: White, Black plus Intermediate and Neutral Bases. The product can be colored with the Istant COLOUR Professional tinting system



APPLICATION

Brush, roller or by spray.



THINNING

With mineral turpentine or synthetic thinner

Brush, roller: 2-3% - Spray: 4-5%.



AVERAGE SPREAD RATE

10 - 12 sq.m./litre per coat



DRYING TIME AT 25° C

1 - 2 hours, dust free

4 - 6 hours, touch dry

Recoat time: after 24 hours



SPECIFIC GRAVITY

1320 & plusmn 20 g/



VISCOSITY

(DIN Cup 4, 20°C): 180"



ADVICES

It is important to respect the drying time of the primer or between coats to avoid a removal effect when applying the new coat over the previous one.



PAKAGING

containers lt.0.75x6 units; lt.2.5x2 units;



DRY SOLID CONTENTS

(%): 63 & plusmn 1



V.O.C. (Directive 2004/42/CE)

295 g/l; Cat. D BS (Max. Value 300 g/l)

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

