


Aditop

Technical Data Sheet

Washable mid-sheen emulsion paint for interiors and exteriors

A wash resistant, mid-sheen emulsion paint for interiors and exteriors that provides a high resistance to humidity and weathering. The advanced formula and quality raw materials used will ensure a fine finish with a delicate silky look.



Ver. 1



INTENDED USE

Any normal paintable interior or exterior wall surface. It can also be used to decorate wood, terracotta and wallpaper surfaces.



SURFACE TREATMENT

Surfaces to treat must be sound, dry, clean, even and free from any trace of loose friable material. For all new, exterior unpainted walls or for weak substrates where consolidation is required, a priming coat of MURISOL is recommended. For walls with existing old paint, remove all weak or flaking paint, restore surface defects and apply a priming coat of ADIFIX.



COLOR

Supply colour: White



APPLICATION

Brush, roller or spray.



THINNING

With water.

Brush, roller: 1st coat 30 - 35%; 2nd coat 25 - 30%.

Spray: 30 - 35%.



AVERAGE SPREAD RATE

10 - 12 sq.m./litre per coat



DRYING TIME AT 25° C

3 - 4 hours, touch dry

Recoat time: 6 - 8 hours



SPECIFIC GRAVITY

1500 ± 10 g/l



VISCOSITY

(Brookfield 20°C): 9000-12000 mPa·s



ADVICES

Do not apply with air and surface temperatures below 5°C. or above 28°C. The thinning water should be added gradually, mixing thoroughly and continuously, especially in case of coloured product. Ensure that the substrate to be painted is sufficiently smooth and well finished to enhance the sheen effect of this paint.



PAKAGING

containers lt. 14;



DRY SOLID CONTENTS

(%): 60 ± 1



V.O.C. (Directive 2004/42/CE)

26 g/l; Cat. A BA (Max. Value 30 g/l)

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

