

# Desiré Chantal



Ver. 1



## Technical Data Sheet

### Pearly metallic, fleck based decorative effect finish

DESIRÉ CHANTAL is the new and exciting variant of the Adicolor decorative fleck paint range. Strikingly colored, pearly metallic flecks readily available in the latest fashion colors: sky blue, peach, pink, green, grey and lavender, all enriched with attractive fine silver micro-granules. A truly fascinating and luminous finish that will add splendor and charm to any interior space.



#### INTENDED USE

Any normal, paintable interior wall surface, either Gypsum plaster based or rendered masonry.



#### SURFACE TREATMENT

Ensure that the surface is clean, dry and free from peeling paint or any substance that may compromise adhesion. In case of old, powdery walls or in presence of weak paint, apply a coat of ADIFIX primer thinned as specified and allow to dry. Roller or brush apply 1 or 2 base coats of FONDO UNIVERSALE, colored with the same Adicolor TINTER to be used for the finish (1 Tinter in 2lt of product) and thinned with 20-30% of water. Let dry for 5-6 hours before applying the finish.



#### COLOR

Add the specified quantity of Adicolor TINTER to the Desiré Chantal base color as indicated on the relative color chart and stir delicately until well blended. We have used 1/3 of Tinter in 1 litre of finish. The quantity of Tinter can be increased should a deeper tone be desired.



#### APPLICATION

Use the special DESIRE' brush and apply unevenly to the surface using short, crossed strokes, flipping and overlapping each time. Start applications from the top corner of the wall and work downwards, covering an area of approx. 3 to 5 sq.m at a time, according to the specific conditions. After about 10-15 minutes from application, when the product has just started to dry, lightly pass the Desiré Distender blade over the product in crossed movements to flatten the raised particles and reach the desired final effect.



#### THINNING

Ready to use or with max.5% water



#### AVERAGE SPREAD RATE

Spread rate (per coat): 15 to 18 m<sup>2</sup>/litre



#### DRYING TIME AT 25° C

2 to 3 hours, touch dry; 1 day, thoroughly dry



#### SPECIFIC GRAVITY

1040 ± 20 g/l



#### VISCOSITY

(Brookfield 20°C): 8000 to 10000 mPa.s



#### V.O.C. (Directive 2004/42/CE)

Cat. L BA - Direttive 2004/42/CE - Val Max.: 200 g/l - Val Eff.: 28 g/l

CONTIENE MISCELA DI 5-CLORO-2METIL-2H-ISOTIAZOL-3-ONE[EC NO.247-500-7];2-METIL-2H-ISOTIAZOL-3-ONE[EC NO. 220-39-6](3:1). PUO' PROVOCARE REAZIONE ALLERGICA

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

