

Shadé L·R



Ver. 1



Technical Data Sheet

The bold and striking metallic paints

Shadé is a striking and eye-catching, waterborne metallic paint that will evoke luxury and subtle contemporary sophistication to any wall, trim, column or other decorative element. It is available in either type "L" Smooth, used like a rich enamel paint, or in type "R" to achieve a lightly textured effect. Each type is supplied in 4 bases: Gold, Silver, Copper and Bronze, that can in addition be easily tinted to a broad range of colors adding the Adicolor Tinters. Hard wearing and easy to apply, Shadé is ideal to add vibrant color and visual richness to living spaces in homes, hotels, stores, offices and other interiors



INTENDED USE

Any normal, paintable interior wall surface, either Gypsum plaster based or rendered masonry.



SURFACE TREATMENT

Walls: Ensure that the surface is clean, dry and free from peeling paint. In case of old and powdery walls or in presence of weak paint, apply a coat of ADIFIX primer thinned as specified and allow to dry. Using a short-pile roller, apply one or two base coats of FONDO UNIVERSALE thinned with 20-30% of water. Let dry for 5-6 hours before applying the finish.

Wood: Apply 1 or 2 coats of ADIPAC. Iron: Apply a coat of ANTIRUST. Pvc, aluminum, zinc: 1 or 2 coats of FUND FLEX.



COLOR

Add the specified quantity of Adicolor TINTER to the SHADÉ L or R in Silver, Gold, Copper or Bronze base as indicated on the relative color chart and stir thoroughly until well blended.



APPLICATION

SHADÉ "L": Apply the product with a shortpile roller. Generally two coats are sufficient for a good opacity. In the second coat, remember to give a very light roll always from the top down to get a uniform finish. Excellent results can be achieved with a spray application, in such case thin with about 10 to 12% water. Application SHADÉ "R": First coat by roller. Second coat with the special Sandé brush or by rag stippler to achieve the desired texture.



THINNING

SHADÉ "L": ready to use. (With 10 to 12% water for spray application) SHADÉ "R": 1st coat 10-15% water; 2nd coat undiluted



AVERAGE SPREAD RATE

Spread rate (per coat):
SHADÉ "L": 10 to 12 m²/litre SHADÉ "R": 6 to 8 m²/litre.



DRYING TIME AT 25° C

4 to 6 hours minimum



SPECIFIC GRAVITY

"L" 1160-1250 +/- 30 g/l "R" 1130-1145 +/- 30 g/l, it depends on color



VISCOSITY

(Brookfield à 27°C): "L" 2800 to 3800 mPa.s - "R" 11000-13000



V.O.C. (Directive 2004/42/CE)

Cat. L BA - Direttive 2004/42/CE - Val Max.: 200 g/l - Val Eff.: 44 g/l

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

