

Velox-Ox

Technical Data Sheet

Antirust gel.form enamel paint

Prime quality, antirust enamel paint in gel form. It acts both as primer and top coat and can be given even over rust and in presence of humidity. Easy to apply, non-drip formula.



Ver. 1



INTENDED USE

Finish coat for metal but also suitable for timber and masonry surfaces.



SURFACE TREATMENT

Ensure that the surface is free from any loose particles of rust. VEL-OX can be applied directly to the surface even without sanding.



COLOR

Available in 10 standard stock colors



APPLICATION

Brush or roller.



THINNING

Ready to use.



AVERAGE SPREAD RATE

12 - 14 sq.m./litre per coat



DRYING TIME AT 25° C

2 - 3 hours, dust free

6 - 8 hours, touch dry

Recoat time: after 12 hours



SPECIFIC GRAVITY

1100 - 1280 g/l

according to the color



VISCOSITY

thixotropic gel



ADVICES

Even though no sanding is required, it is advisable to clean the surface from eventual loose flakes of rust .



PAKAGING

containers lt.0.75x6 units;



DRY SOLID CONTENTS

(%): 64 ± 1



V.O.C. (Directive 2004/42/CE)

435 g/l; Cat. I BS (Max. Value 500 g/l)

Any information supplied whether verbal or in writing, is for guidance only as conditions and feasibility of use may be influenced by external factors beyond our control and is therefore given in good faith but without warranty. Adicolor reserves the right to modify any data and information without notice. Our technical service is available for any further detailed information.

