

TECHNICAL DATA SHEET **WOOL**

PRODUCT

WOOL

DESCRIPTION

A waterborne decorative effect finish that imitates the texture of a bouclé woolen fabric.

INTENDED USE

For interior decoration on all types of substrates such as rendered walls, plasters, plasterboards, wood, etc. appropriately treated.

SURFACE PREPARATION

The surface to treat must be clean, dry and perfectly sound. Smooth surfaces give a more typical effect finish. In case of new untreated walls, or for old powdery walls, apply a coat of ADIFIX thinned as specified and once dry, roller apply one or two basecoats of White FONDO UNIVERSALE thinned with 20-30% water.

On new untreated walls: Remove all traces of dust, dirt and any parts non perfectly adherent. Apply a coat of ADIFIX primer thinned as specified and once dry, roller apply one or two basecoats of White FONDO UNIVERSALE thinned with 20-30% water.

On pre-painted surfaces: Verify that the condition of the existing paint is in good state without signs of flaking, bubbling or other incoherency. In such case repair where necessary and proceed as described for new untreated walls. If in good condition, apply one or two basecoats of White FONDO UNIVERSALE thinned with 20-30% water.

INSTRUCTIONS FOR USE

Application: Apply WOOL by brush unevenly to the surface using vertical strokes, (or according to the desired direction of the design), starting from a top corner of the wall. After about 15 or 20 minutes, in any case before drying, create the bouclé effect by dragging the TESSUTI ADICOLOR tool down the wall from top of bottom. To achieve the typical woven effect, repeat the previous application, but applying the product in horizontal strokes and dragging the tool across the wall horizontally

Advices: Do not apply with air and surface temperatures below 5°C. or above 28°C.
 Protect from freezing and store under cover.
 Clean tools with warm water.

TECHNICAL DATA

Average yield	About 8 - 10 m ² /L per coat
Thinning	Ready to use or, in case of necessity, with max. 5-10% of water
Drying time at 25°C	Touch dry after about 4 - 6 hours.
Recoat time	After at least 10-12 hours
Average Density	1.020 ± 0.020 kg/L
V.O.C. (European Dir. 2004/42/CE)	10 g/L; cat L BA limit max 200

PACKAGING

Containers of: 2 L

SUPPLY COLOR/S

8 ready mixed colors : WL01 – WL02 – WL03 – WL04 – WL05 – WL06 – WL06 – WL07 – WL08