# TECHNICAL DATA SHEET

MYLAK

Solvent based, ready to use enamel paint with antirust properties

# **PRODUCT DESCRIPTION**

Solvent-borne synthetic enamel paint that features good brushability, flow and coverage. Thanks to its specific formulation, the product gives the surface an anti-rust effect, guarantees long life duration and resistance to yellowing.

### **INTENDED USE**

Destination:	Specific for:
Interiors	Iron and wood
Exteriors	Any other adequately prepared support

#### SURFACE PREPARATION

The correct surface preparation of the substrate will guarantee the best results in terms of product yield, appearance and resistance in time of the finish

#### <u>IRON</u>

- New iron: Clean and degrease the surface to remove all possible traces of dust or dirt. Treat with a priming coat
  of ADIMIN or ANTIRUST.
- Iron with old paint: Clean, degrease and brush the surface to remove any loose or weak paint then sand away any existing rust. Treat the support with a priming coat of ADIMIN or ANTIRUST.

#### **DIFFICULT SUBSTRATES** (galvanized metals, aluminum, PVC...)

• Clean and degrease the surface to remove all possible traces of dust or dirt. Prime the support with **FUNDFLEX**.

#### WOOD

- New wood: Clean the surface to remove all possible traces of dust or dirt. Prepare the support with ADIPAC
- Wood with old paint: Remove weak paint, sand and clean. Prepare the support with ADIPAC.

The information reported herein is the result of our best experience and technical knowledge to date and is given in good faith and for guidance only. ADICOLOR cannot be held responsible for the actual use of the product since the application is influenced by many factors and is carried out beyond our control. The data and information herein may be subject to changes, even without notice, as a result of any technical development. This technical data sheet cancels and replaces any existing previous version.



# Additional information:

- The substrates must in every case be sound, dry and clean.
- Remove all possible traces of dust, dirt or other impurities before the application.
- The nature of the support can change the final appearance of product.

#### **INSTRUCTIONS FOR USE**

#### Tools used for application

- Brush
- Roller
- Spraying equipment

#### **APPLICATION METHOD**

It is recommended to apply the product in two coats.

#### **TECHNICAL SPECIFICATIONS**

<b>6</b> 3	Indicative spread rate per coat (m²/ℓ)	-	-	8 to 10
۵	Thinning (%)	-	-	Ready to use
	Touch dry (at 25°C)	-	hours	4 to 6
	Totally dry	-	hours	24
19 19 19 19	Recoat time	-	hours	12
	Density (kg/l, ±0.02)	ISO 2811	at 20°C	White Gloss: 1.200 White Satin: 1.310 White Matt: 1.310
•	Viscosity Brookfield (mPa·s)	ISO 2555	at 20°C	White Gloss: 1,000 to 1,200 White Satin: 2,300 to 2,500 White Matt: 2,300 to 2,500
N/Z	Gloss (60°)	-	-	Gloss: 80 to 90 Satin: 15 to 25 Matt: < 7
۲	Solid contents by weight (%, ±1)	-	-	72

\* the data herein reported refer to measurements made at the end of the production process.

#### TOOL CLEANING

• Clean working tools immediately after use with white spirits, synthetic or nitro thinner.

The information reported herein is the result of our best experience and technical knowledge to date and is given in good faith and for guidance only. ADICOLOR cannot be held responsible for the actual use of the product since the application is influenced by many factors and is carried out beyond our control. The data and information herein may be subject to changes, even without notice, as a result of any technical development. This technical data sheet cancels and replaces any existing previous version.

# WARNINGS AND ADDITIONAL INFORMATION

- Do not apply with air and surface temperatures below 5°C and above 28°C.
- The drying times indicated may vary in relation to the relative humidity and the existing temperature.
- Carefully verify spread rates and the surface area to be coated to avoid running short of product during the working
  process. This will also reduce the risk of eventual differences in tones.
- The spread rates and yields of the product are given as guidance only and may vary notably according to the substrate condition and the application method used.
- Stir the product thoroughly before use.
- Remove masking tapes before total drying of the product.
- It is recommended to always carry out a sample test on the specific surface before starting the final work.

#### HANDLING AND STORAGE

- Consult the relative **Safety Data Sheet** for the detailed user's health and safety information.
- Use the product in accordance with your current health and safety legislation regulations in force.
- Do not disperse the packaging in the environment
- Store the undiluted product, in original well sealed containers, in a cool and dry area, sheltered from frost and sources of heat.

# COLORS

#### Colors available:

Gloss finish		Satin finish	Matt finish
White Black		White Black	White Black
28 – Pearl White	15 - Green		
o2 – Cream	34 – Lawn Green		
o3 – Pale Beige	16 – Dark Green		
o6 – Chrome Yellow	20 – Greece Blue		
07 - Orange	22 - Ice		
o8 – Bright Red	23 – Light Grey		
09 - Hazelnut	39 – Warm Grey		
10 - Brown	24 – Grey		
11 – Dark brown	25 – Dark Grey		

 Reference color-guides

 The specific product color-guide

- When using multiple cans for the same job, we recommend to mix the relative products together before use. We also recommend to use products from the same batch numbers for the same application area.
- The colors presented in our catalogues are for guidance only, even when true product applications are shown. Colors may vary notably in relation to the application, the substrate, light reflectance and the environment.
- It is recommended to test and validate colors before carrying out the final job in order to avoid any disputes.

The information reported herein is the result of our best experience and technical knowledge to date and is given in good faith and for guidance only. ADICOLOR cannot be held responsible for the actual use of the product since the application is influenced by many factors and is carried out beyond our control. The data and information herein may be subject to changes, even without notice, as a result of any technical development. This technical data sheet cancels and replaces any existing previous version.